

Magnetic properties of the chain antiferromagnet RbFeSe₂

Seidov Z.^{1,2}, **Krug von Nidda H.-A.**¹, **Tsurkan V.**^{1,3}, **Filipova I.**³, **Günther A.**¹,
Aliyev M.⁴, **Vagizov F.**⁵, **Kiiamov A.**⁵, **Tagirov L.**^{5,6}, **Gavrilova T.**⁶ and **Loidl A.**¹

¹*Experimental Physics V, Center for Electronic Correlations and Magnetism,
University of Augsburg, Augsburg (Germany)*

²*Institute of Physics, Azerbaijan Academy of Sciences, Baku (Azerbaijan)*

³*Institute of Applied Physics, Academy of Sciences of Moldova, Chisinau (Moldova)*

⁴*Baku State University, Chair of the Solid State Physics, Baku (Azerbaijan)*

⁵*Institute of Physics, Kazan Federal University, Kazan (Russia)*

⁶*E.K. Zavoisky Physical-Technical Institute, Russian Academy of Sciences, Kazan (Russia)*
zsyu@rambler.ru

Single crystals of the ternary iron selenide RbFeSe₂ (with linear chains of FeSe₄ tetrahedra) have been investigated by means of X-ray diffraction, Mössbauer, magnetic susceptibility and specific heat measurements. Our Mössbauer experiments performed from room temperature (RT) down to 4.2 K have shown that the compound undergoes a magnetic phase transition near 248 K. Mössbauer parameters determined in the entire temperature range indicate that iron in RbFeSe₂ is in ferric (trivalent) state having strong covalent bonding to selenium ligands. The measured hyperfine field of 216 kOe at 4.2 K is quite reduced compared with that in high-spin ferric compounds. The SQUID susceptibility and specific heat measurements confirm that RbFeSe₂ exhibits 3D collinear antiferromagnetic order below $T_N = 248$ K with magnetic moments oriented perpendicular to the chain direction. The strict linear increase of the susceptibility to high temperatures strongly suggests a one-dimensional metallic character of RbFeSe₂ along the chains.




Fig. 1. Mössbauer spectra at RT and 80 K (top), hyperfine field vs temperature (bottom)




Fig. 2. Magnetic susceptibility vs temperature (top), specific heat vs temperature (bottom)