

Contents lists available at ScienceDirect

## **Electrochemistry Communications**



journal homepage: www.elsevier.com/locate/elecom

# Molecular oxygen as a mediator in the electrosynthesis of gold nanoparticles in DMF



© 2016 Elsevier B.V. All rights reserved.

### Vitaliy V. Yanilkin<sup>a,\*</sup>, Natalya V. Nastapova<sup>a</sup>, Gulnaz R. Nasretdinova<sup>a</sup>, Rezeda R. Fazleeva<sup>a</sup>, Yuri N. Osin<sup>b</sup>

<sup>a</sup> A.E. Arbuzov Institute of Organic and Physical Chemistry, Kazan Scientific Center, Russian Academy of Sciences, Arbuzov St. 8, 420088 Kazan, Russia <sup>b</sup> Kazan Federal University, Interdisciplinary Center for Analytical Microscopy, Kremlevskaya St. 18, 420018 Kazan, Russia

#### ARTICLE INFO

#### ABSTRACT

particles by reduction of Au(I) in DMF.

Article history: Received 29 April 2016 Received in revised form 16 May 2016 Accepted 17 May 2016 Available online 18 May 2016

#### Keywords: Electrochemical synthesis Molecular oxygen Mediator Au nanoparticle

#### 1. Introduction

Electroreduction of metal ions and complexes is quite rarely used for electrosynthesis of in-demand [1-7] metal nanoparticles (MNP) in solution bulk. The main factor limiting the use of electrochemistry is precipitation of generated metal on an electrode surface. Therefore, in all the methods developed for MNP electrosynthesis in solution bulk, the deposition problem is solved in some way. In the pulse sonoelectrochemistry method [8-10], this problem is solved by combining the process of MNP generation on an electrode surface during electroreduction for a short time with its subsequent transfer into the solution by sonication of the working electrode. In the method by Reetz et al. [11–15], electroreduction of ions is carried out in aprotic organic media using salts of surfactant cations, such as tetraalkylammonium or phosphonium, as a supporting electrolyte. For these purposes we have proposed a method of mediated electrosynthesis [16-25] which differs from the above-mentioned electrochemical methods in such a way that the step of metal ion reduction is moved from the electrode surface into the solution bulk. In this case, a mediator is reduced on the cathode and the reduced form of the mediator diffuses into solution bulk where it reduces the metal ion or complex. Thus, deposition of the metal on the electrode is completely prevented or minimized. The feasibility of the method and its efficiency have been recently demonstrated by the examples of preparation of Pd [16-20], Ag [21-23], Co [24], Au [25] NP in the absence and presence of stabilizers in aqueous, aqueous-organic and non-aqueous media from metal salts and complexes, or from metal ions generated in situ in solution upon dissolution of a metal anode during electrolysis. The method is equally efficient with soluble ions and complexes ([PdCl<sub>4</sub>]<sup>2-</sup>, Ag<sup>+</sup>, AuCl, [CoCl<sub>4</sub>]<sup>2-</sup>) and insoluble metal salts (AgCl, spherical AgCl@CTAC NP), irrespective of whether reduction of the mediator on the electrode is easier or harder than reduction of the metal substrate. Methylviologen, free or fixed on calix[4]resorcine

platform, and anthracene were used as a mediator.

The possibility of using of molecular oxygen as a mediator in electrosynthesis of metal nanoparticles by reduction

of their ions and complexes in aprotic media was demonstrated by the example of electrosynthesis of gold nano-

In this paper, we report on the possibility of using of molecular oxygen as a mediator in electrosynthesis of MNP by reduction of metal salts and complexes in aprotic media by the example of electrosynthesis of AuNP in DMF. Oxygen is a non-polluting gas that is dissolved from the air in organic media under normal conditions at concentrations sufficient for a mediator [26]. Thus, the need of using of other mediators and subsequent removal of them from MNP are eliminated.

#### 2. Experimental Section

**Chemicals.** AuCl (Alfa Aesar), polyvinylpyrrolidone (PVP) 40,000 (Alfa Aesar), the supporting electrolyte Bu<sub>4</sub>NCl (Fluka), DMF (Alfa Aesar) were used as purchased without additional purification.

**The CV recordings** were done with a P-30J potentiostat in DMF/ 0.1 M Bu<sub>4</sub>NCl. The working electrode was a glassy carbon (GC) disk electrode ( $\emptyset = 2.0$  mm) pressed into glass. The electrode was cleaned by mechanical polishing before each measurement. Platinum wire was a counter electrode. The potentials were measured relative to the aqueous saturated calomel electrode (SCE). The aqueous SCE was

<sup>\*</sup> Corresponding author. E-mail address: yanilkin@iopc.ru (V.V. Yanilkin).

connected by a bridge filled with supporting solution. The temperature was 295 K.

**The preparative reduction** of the solution (10 ml) containing 1.5 mM AuCl (3.5 mg), ~2.9 mM O<sub>2</sub>, 8.33 g/l PVP (83.3 mg), 0.1 M Bu<sub>4</sub>NCl (417 mg) was carried out in a cell separated with a porous glass diaphragm in potentiostatic mode (-1.10 V) at room temperature (T = 295 K). During the electrolysis, the solution was stirred with a magnetic stirrer. A GC plate (S = 5.6 cm<sup>2</sup>) was used as the working electrode. The reference and auxiliary electrodes were used as in CV experiments. After the electrolysis (Q = 1.0 F with respect to AuCl) solid AuCl (poorly soluble in DMF) disappeared. When the electrolysis was over, the solution was studied by CV on the indicator GC disk electrode ( $\emptyset$  = 2.0 mm) directly in the electrolysis cell.

**TEM** analysis of NP was carried out using a Hitachi HT7700 Excellence transmission electron microscope. Sample preparation: 10  $\mu$ l of the suspension was placed on a Formvar<sup>TM</sup>/carbon coated 3 mm copper grid, which was then dried at room temperature. After complete drying, the grid was placed into a transmission electron microscope using special holder for microanalysis. Analysis was held at an accelerating voltage of 80 kV in TEM mode.

**SEM** analysis and **DLS** measurements were performed as described in [25].

**UV–visible spectra** were recorded on a Perkin-Elmer Lambda 25 spectrometer.

#### 3. Results and Discussions

The CV curves of molecular oxygen (C ~ 2.9 mM) dissolved in DMF/ 0.1 M Bu<sub>4</sub>NCl medium under ordinary conditions in contact with air contain two reduction peaks in full accordance with the literature data [27]. The first of them is chemically reversible and the second is irreversible (Fig. 1A). The first peak is due to one-electron reduction of oxygen to the radical anion (superoxide ion). Reversibility of the peak indicates sufficient stability of generated O<sub>2</sub>•<sup>-</sup> under these conditions. When PVP widely used as a MNP stabilizer is added to the solution, the reversibility of the peak remains (Fig. 1A). One-step reduction of Au(I) (AuCl or  $[AuCl_2]^{-}$  [25]) is irreversible in the absence of oxygen, is significantly easier than reduction of oxygen and does not depend on the presence of PVP in the solution (Fig. 1A). Unlike aqueous media [25], metallic gold generated and deposited on the electrode is not oxidized in the available region of potentials. The morphology of the CV curve of O<sub>2</sub> and Au(I) mixture corresponds to the additive curve of individual components. The sum of current of the one-step reduction peaks of Au(I) and  $O_2$  is also equal to the additive value. This means that quantitative reduction of Au(I) to Au<sup>0</sup> and of  $O_2$  to  $O_2^{\bullet}$  occurs at the potentials of the first peak of oxygen reduction. However, CV curves do not answer the question: how is Au(I) reduced – by mediated process or directly on the electrode.

Preparative electroreduction of Au(I) (1.5 mM AuCl, ~2.9 mM O<sub>2</sub>, 8.33 g/l PVP) was performed in DMF/0.1 M Bu<sub>4</sub>NCl medium in a diaphragm cell at controlled potential of the first stage of oxygen reduction to  $O_2^{\bullet-}$  (E = -1.10 V). Currents are gradually decreased from 6.1 to 2.5 mA during the electrolysis (7 min 15 s). The initially yellow solution became colorless, it remained homogeneous, and formation of a precipitate was not observed visually. Such change of the solution color is not typical of the formation of AuNP in solution. The AuNP solutions are usually colored [6,25].

After passing 1.0 F with respect to Au(I), the peak of Au(I) reduction is absent and only the initial intensity peaks of oxygen reduction and reoxidation (Fig. 1B) are present on the CV curves. The cathode weight is kept constant. Therefore, after passing the theoretical amount of electricity, quantitative transformation of Au(I) to very soluble Au<sup>0</sup> occurs. The generated Au<sup>0</sup> is not deposited on the electrode and is electrochemically inactive in the available potential range. Because the electrolysis is carried out at the potentials of reduction of O<sub>2</sub> the reduction currents of which are significantly higher than for Au(I), and only reduction of Au(I) takes place as the result, it is evident that oxygen mediated electroreduction of Au(I) occurs in the solution bulk (Scheme 1).

In the resulting electrolyte (solution 1), NP with a mean hydrodynamic diameter of 10 and 69 nm are recorded by DLS, and the largest number of particles has a size of 7 nm (PdI =  $0.479 \pm 0.017$ ), while UV-visible spectrum shows the very weak absorption band of AuNP at 550 nm (Fig. 2). However, an attempt to precipitate NP by centrifugation (15,000 rpm for 2 h) failed. Because of this, DMF was removed from part of solution 1 by water-jet pump vacuum, and dry residue was dispersed in ethanol (solution 2) and water (solution 3) by sonication. The solution 1 remained colorless for a long time upon storage in the dark at room temperature, but then slowly began to become violet (color of AuNP) and after 15 days was intense violet. In this case in the solution 1, NP with a mean hydrodynamic diameter of 30 and 121 nm are recorded by DLS, and the largest number of particles has a size of 24 nm (PdI =  $0.269 \pm 0.003$ ). The UV-visible spectrum contains the intense absorption band of AuNP with  $\lambda_{max} = 585$  nm (Fig. 2). Similar conversions of the solutions 2 and 3 occurred more rapidly for 48 and 8 h, respectively. After precipitation from all three solutions of AuNP by centrifugation (15,000 rpm for 2 h), twice ethanol washing and subsequent precipitation, NP was dispersed in ethanol (solutions 1', 2' and 3' respectively) and was investigated by complex of methods.

In the resulting *solution* 1', 2' and 3', NP with a mean hydrodynamic diameter of 26 and 121 nm, 104 and 330 nm, 58 and 216 nm respectively are recorded by DLS (Fig. 2B), the largest number of particles has a



**Fig. 1.** (A) CV curves of (1)  $O_2$  (~2.9 mM) (2) the PVP (8.33 g/l) +  $O_2$  (~2.9 mM) system and (3) the AuCl (1.5 mM) + PVP (8.33 g/l) system; (B) CV curves of the AuCl (1.5 mM) + PVP (8.33 g/l) +  $O_2$  (~2.9 mM) system (1) before and (2) after reduction at - 1.10 V (Q = 1.0 F with respect to AuCl). DMF/0.1 M Bu<sub>4</sub>NCl.  $\nu$  = 100 mV/s.



Scheme 1. Oxygen mediated electrosynthesis of AuNP.

size of 14 and 23 nm (PdI =  $0.296 \pm 0.008$ , solution 1'), 67 nm (PdI =  $0.373 \pm 0.029$ , solution 2'), 46 and 99 nm (PdI =  $0.278 \pm 0.028$ , solution 3'). The UV-visible spectra (Fig. 2A) show two absorption bands of AuNP at 620 and 870 nm for the solution 1', the intense absorption band at 550 nm and less intense band at 700 nm for the solution 2', and the broad absorption band of AuNP, which can be interpreted as a

sum of a lot of bands with  $\lambda_{max}$  in the range of 550 and 610 nm, for the solution 3'.

In the SEM image of the sample from the *solution* 1', V-shaped NP (the length is 135  $\pm$  61 nm, the width is 48  $\pm$  17 nm, Fig. 3A) and polyhedral NP with the average size of 70  $\pm$  46 nm are recorded. According to TEM-micrograph (Fig. 3B) and energy-dispersive spectrum (Fig. 3C), all NP correspond to metallic gold stabilized in the PVP shell. The length and the width of the metal in the V-shaped particles is 112  $\pm$  53 nm and 58  $\pm$  22 nm, respectively, the average size of metal in other AuNP is 46  $\pm$  14 nm (Fig. 3).The differences in average size of polydisperse particles obtained by different methods are due to the fact that the size of individual metal nanoparticles is measured by SEM, and the average diameter of metal particles in PVP with solvation shell and their aggregates in the solution are measured by DLS.

In the SEM image of the sample from the *solution 2'*, there is the large number of NP in the form of irregular polyhedron, as well as hexagonal NP with larger size (Fig. 3A). According to TEM micrograph (Fig. 3B) and the energy-dispersive spectrum (Fig. 3C), all NP are metallic gold



Fig. 2. (A) UV-visible spectrum and (B) size distribution diagram (DLS) of AuNP in the investigated systems.



Fig. 3. (A) SEM, (B) TEM image and (C) energy-dispersion spectrum (Ti from the support) of AuNP in the investigated systems.

stabilized in the PVP shell. The average size of metal is  $56 \pm 25$  nm in AuNP in the form of polyhedrons, and is  $105 \pm 29$  nm in hexagonal AuNP. It is known [5,28,29] that wavelength of absorption band increases with an increase in the NP size. Thus, the band at 550 nm corresponds to the polyhedrons, and the band at 700 nm corresponds to hexagonal NP.

The polydisperse spherical NP are present and hexagonal NP are absent in the SEM image of the sample from the *solution* 3' (Fig. 3A). According to TEM micrograph (Fig. 3B) and the energy-dispersive spectrum (Fig. 3C), NP correspond to metallic gold with the average size of  $13 \pm 8$  nm stabilized in the PVP shell.

#### 4. Conclusions

Thus, the final result of Au(I) electroreduction in DMF at potentials of O<sub>2</sub> reduction to O<sub>2</sub>•<sup>-</sup> is AuNP with different sizes and shapes depending on the method of treatment of the solution after the electrolysis. It should be noted, that no visual change occurs in the initial electrolyte after electrolysis in DMF, as well as in ethanol and aqueous solutions of the initial system (1.5 mM AuCl, 8.33 g/l PVP, 0.1 M Bu<sub>4</sub>NCl), for a week. The results as a whole show that during the electrolysis oxygen mediated electroreduction of Au(I) occurs in the solution bulk to form ultra-small NP of amorphous gold (Scheme 1), stable for a long time in the presence of PVP and Bu<sub>4</sub>NCl in DMF. According to [5,28,29], the absence of absorption band in the visible spectrum means that the metal particle size is less than 2 nm. The rate of the subsequent formation of Au crystal nuclei and growth of crystals depend on the microenvironment of NP. The lowest rate is observed in DMF, the largest is in water, and ethanol is intermediate. So the shape and the size of the resulting NP are different. In DMF nucleation occurs very slowly, while the crystal growth proceeds faster, but still under kinetic control. Because of this, the crystal growth in certain directions occurs at a higher rate, so V-shaped AuNP are formed along with polyhedron. Removal of DMF and followed dispersion in ethanol result in the destruction of the stabilizing shell of AuNP and the process acceleration of the nucleation, as well as the growth of gold crystals in all directions. This leads to another set of AuNP: hexagonal particles, as well as malformed polyhedral particles, are formed. Dispersion in water leads to an even greater acceleration of these processes, so the crystal growth in all directions occurs almost at the same rate, and as a result AuNP with spherical shape are formed. AuNP obtained by methylviologen mediated electrosynthesis in the presence of PVP in an aqueous medium [25] had the same shape and almost the same size.

#### Acknowledgment

The authors would like to acknowledge the financial support from RSF (grant no. 14-23-00016).

#### References

- A.D. Pomogaylo, A.S. Rosenberg, I.E. Uflyand, Nanoparticles of Metals in Polymers, Khimia, Moscow, 2002.
- [2] V.I. Roldughin, Quantum-size colloid metal systems, Russ. Chem. Rev. 69 (2000) 821–843.
- [3] M.C. Daniel, D. Astruc, Gold nanoparticles: assembly, supramolecular chemistry, quantum-size-related properties, and applications toward biology, catalysis, and nanotechnology, Chem. Rev. 104 (2004) 293–346.
- [4] I.P. Suzdalev, Nanotechnology. Physicochemistry of Nanoclusters, Nanostructures and Nanomaterials, KomKniga, Moscow, 2006.
- [5] V.V. Volkov, T.A. Kravchenko, V.I. Roldughin, Metal nanoparticles in catalytic polymer membranes and ion-exchange systems for advanced purification of water from molecular oxygen, Russ. Chem. Rev. 82 (2013) 465–482.

- [6] L.A. Dykman, V.A. Bogatyrev, S.Y. Shchyogolev, N.G. Khlebtsov, Gold Nanoparticles. Synthesis, Properties and Biomedical Applications, Nauka, Moscow, 2008.
- [7] B.I. Kharisov, O.V. Kharissova, U. Ortiz-Mendez, Handbook of Less-common Nanostructures, CRC Press, 2012.
- [8] V. Saez, T.J. Mason, Sonoelectrochemical synthesis of nanoparticles, Molecules 14 (2009) 4284–4299.
- [9] J. Zhu, S. Liu, O. Palchik, Y. Koltypin, A. Gedanken, Shape-controlled synthesis of silver nanoparticles by pulse sonoelectrochemical methods, Langmuir 16 (2000) 6396–6399.
- [10] J. Reisse, T. Caulier, C. Deckerkheer, O. Fabre, J. Vandercammen, J.L. Delplancke, R. Winand, Quantitative sonochemistry, Ultrason. Sonochem. 3 (1996) 147–151.
- [11] M.T. Reetz, W. Helbig, Size-selective synthesis of nanostructured transition metal clusters, J. Am. Chem. Soc. 116 (1994) 7401–7402.
- [12] J.A. Becker, R. Scha¨fer, R. Festag, W. Ruland, J.H. Wendorff, J. Pebler, S.A. Quaiser, W. Helbig, M.T. Reetz, Electrochemical growth of superparamagnetic cobalt clusters, J. Chem. Phys. 103 (1995) 2520–2527.
- [13] M.T. Reetz, S.A. Quaiser, C. Merk, Electrochemical preparation of nanostructured titanium clusters: characterization and use in McMurry-type coupling reactions, Chem. Ber. 129 (1996) 741–743.
- [14] M.T. Reetz, W. Helbig, S.A. Quaiser, U. Stimming, N. Breuer, R. Vogel, Visualization of surfactants on nanostructured palladium clusters by a combination of STM and high-resolution TEM, Science 267 (1995) 367–369.
- [15] M.T. Reetz, M. Winter, R. Breinbauer, T. Thurn-Albrecht, W. Vogel, Size-selective electrochemical preparation of surfactant-stabilized Pd-, Ni- and Pt/Pd colloids, Chem. Eur. J. 7 (2001) 1084–1094.
- [16] V.V. Yanilkin, G.R. Nasybullina, A.Y. Ziganshina, I.R. Nizamiev, M.K. Kadirov, D.E. Korshin, A.I. Konovalov, Tetraviologen calix[4]resorcine as a mediator of the electrochemical reduction of [PdCl<sub>4</sub>]<sup>2-</sup> for the production of Pd<sup>0</sup> nanoparticles, Mendeleev Commun. 24 (2014) 108–110.
- [17] V.V. Yanilkin, G.R. Nasybullina, E.D. Sultanova, A.Y. Ziganshina, A.I. Konovalov, Methyl viologen and tetraviologen calix[4]resorcinol as mediators of the electrochemical reduction of [PdCl<sub>4</sub>]<sup>2-</sup> with formation of finely dispersed Pd<sup>0</sup>, Russ. Chem. Bull. 63 (2014) 1409–1415.
- [18] V.V. Yanilkin, N.V. Nastapova, G.R. Nasretdinova, R.K. Mukhitova, A.Y. Ziganshina, I.R. Nizameev, M.K. Kadirov, Mediated electrochemical synthesis of Pd<sup>0</sup> nanoparticles in solution, Russ. J. Electrochem. 51 (2015) 951–962.

- [19] S. Fedorenko, M. Jilkin, N. Nastapova, V. Yanilkin, O. Bochkova, V. Buriliov, I. Nizameev, G. Nasretdinova, M. Kadirov, A. Mustafina, Y. Budnikova, Surface decoration of silica nanoparticles by Pd(0) deposition for catalytic application in aqueous solutions, Colloids Surf. A Physicochem. Eng. Asp. 486 (2015) 185–191.
- [20] V.V. Yanilkin, N.V. Nastapova, E.D. Sultanova, G.R. Nasretdinova, R.K. Mukhitova, A.Y. Ziganshina, I.R. Nizameev, M.K. Kadirov, Electrochemical synthesis of nanocomposite of palladium nanoparticles with polymeric viologen-containing nanocapsule, Izv. AN, Ser Chim. 1 (2016) 125–132.
- [21] G.R. Nasretdinova, R.R. Fazleeva, R.K. Mukhitova, I.R. Nizameev, M.K. Kadirov, A.Y. Ziganshina, V.V. Yanilkin, Electrochemical synthesis of silver nanoparticles in solution, Electrochem. Commun. 50 (2015) 69–72.
- [22] G.R. Nasretdinova, R.R. Fazleeva, R.K. Mukhitova, I.R. Nizameev, M.K. Kadirov, A.Y. Ziganshina, V.V. Yanilkin, Electrochemical mediated synthesis of silver nanoparticles in solution, Russ. J. Electrochem. 51 (2015) 1029–1040.
- [23] V.V. Yanilkin, N.V. Nastapova, G.R. Nasretdinova, R.R. Fazleeva, A.V. Toropchina, Y.N. Osin, Methylviologen mediated electrochemical reduction of AgCl – a new route to produce a silica core/Ag shell nanocomposite material in solution, Electrochem. Commun. 59 (2015) 60–63.
- [24] V.V. Yanilkin, G.R. Nasretdinova, Y.N. Osin, V.V. Salnikov, Anthracene mediated electrochemical synthesis of metallic cobalt nanoparticles in solution, Electrochim. Acta 168 (2015) 82–88.
- [25] V.V. Yanilkin, N.V. Nastapova, G.R. Nasretdinova, S.V. Fedorenko, M.E. Jilkin, A.R. Mustafina, A.T. Gubaidullin, Y.N. Osin, Methylviologen mediated electrosynthesis of gold nanoparticles in the solution bulk, RSC Adv. 6 (2016) 1851–1859.
- [26] Solubility Data Series, in: R. Battino (Ed.), Oxygen and Ozone, vol.7, Pergamon, Oxford, 1981.
- [27] C.K. Mann, K.K. Barnes, Electrochemical Reactions in Nonaqueous Systems, Marcel Dekker, Inc., New York, 1970.
- [28] P. Mulvaney, Surface plasmon spectroscopy of nanosized metal particles, Langmuir 12 (1996) 788–800.
- [29] V.A. Bogatyrev, L.A. Dykman, Y.M. Krasnov, V.K. Plotnikov, N.G. Khlebtsov, Differential light scattering spectroscopy for studying biospecific assembling of gold nanoparticles with protein or oligonucleotide probes, Kolloidn. Zh. 64 (2002) 745–755.